



# TNEME-GLAZE SERIES 282

## PRODUCT PROFILE

<b>GENERIC DESCRIPTION</b>	Polyamine Novolac Epoxy
<b>COMMON USAGE</b>	A highly chemical- and solvent-resistant colored novolac glaze coating for walls, floors and other surfaces. Provides improved aesthetics and additional protection against abrasion, impact, and most acids, alkalis and solvents.
<b>COLORS</b>	Available in six standard StrataShield colors: 33GR Gray ANSI No. 61, 46GR Sinker, 42BL Blue Channel, 91GN Balsam, 35GR Black, 28RD Monterrey Tile. Special colors available, please contact your Tnemec representative. <b>Note:</b> Epoxies chalk and yellow with age, extended exposure to UV and artificial lighting. Caution should be taken when selecting white and light pastel colors. Lack of ventilation, incomplete mixing, miscatalyzation or the use of heaters that emit carbon dioxide and carbon monoxide during application and initial stages of curing may cause amine blush, possibly affecting adhesion of subsequent topcoats. Novolacs will stain with extended exposure to certain acids. As a result, darker colors are recommended.
<b>FINISH</b>	Gloss. (Roller application provides an orange peel finish.)

## COATING SYSTEM

<b>SURFACER/FILLER/PATCHER</b>	Series 130, 215, N218, 1254. <b>Note:</b> A repair kit of 201 with Part C fumed silica (S201-0001-TK) is available for small patching/surfacing repairs. For more extensive repairs and additional information, contact your Tnemec representative or Tnemec Technical Services.
<b>PRIMERS</b>	<b>Steel:</b> Series 21, 22, 66, N69, 161. <b>Concrete:</b> Self-priming or Series 201, N222, N222FC, 233, 239, N241. <b>CMU:</b> Self-priming over filled CMU <b>Wall board, Wood &amp; Drywall:</b> Self-priming or Series 201
<b>INTERMEDIATE TOPCOATS</b>	Series 210, N222, N222FC, 233, N237SC, 239, 239SC, 270, 273, 282 Series 282

## SURFACE PREPARATION

	Prepare surfaces by method suitable for exposure and service. Refer to the appropriate primer data sheet for specific recommendations.
<b>HORIZONTAL CONCRETE</b>	Allow new poured-in-place concrete to cure a minimum of 28 days at 75°F (24°C). Verify concrete dryness in accordance with ASTM F 1869 "Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride" (moisture vapor transmission should not exceed three pounds per 1,000 square feet in a 24 hour period), F 2170 "Standard Test Method for Determining Relative Humidity in Concrete using in situ Probes" (relative humidity should not exceed 80%), or D 4263 "Standard Test Method for Indicating Moisture in Concrete by the Plastic Sheet Method" (no moisture present). Note: The testing listed above cannot guarantee avoidance of future moisture related problems particularly with existing concrete slabs. This is especially true if the use of an under slab moisture vapor barrier cannot be confirmed or concrete contamination from oils, chemical spills, unreacted silicates, chlorides or Alkali Silica Reaction (ASR) is suspected.  Prepare concrete surfaces in accordance with NACE No. 6/SSPC-SP13 Joint Surface Preparation Standards and ICRI Technical Guidelines. Abrasive blast, shot-blast, water jet or mechanically abrade concrete surfaces to remove laitance, curing compounds, hardeners, sealers and other contaminants and to provide a minimum ICRI-CSP 3 or greater surface profile. Large cracks, voids and other surface imperfections should be filled with a recommended filler or surfacer. <b>Note:</b> For moisture content exceeding 3 lbs per 1,000 sq ft or relative humidity in excess of 80%, Series 208 or N241 may be substituted for the primer. Refer to the Series 208 or N241 product data sheet for more information.
<b>VERTICAL CONCRETE</b>	When self-priming: Allow new concrete to cure 28 days. Abrasive blast or mechanically abrade concrete to remove laitance, form release agents, curing compounds, hardeners, sealers and other contaminants and to provide surface profile. (Reference SSPC-SP13)
<b>CMU</b>	When self-priming: Allow new mortar to cure 28 days. Surfaces must be clean, dry, sound and free of all contaminants. Level all protrusions and mortar spatter. For pinhole free surface, use recommended surfacer/filler/patcher.
<b>WALL BOARD, WOOD &amp; DRYWALL</b>	Must be clean, dry and free of oil, grease and other contaminants. <b>Note:</b> When using moisture resistant and/or high impact wall board or cement board in wet environments, utilize Series 215 and fiberglass tape or compound suitable for wet environments.
<b>ALL SURFACES</b>	Must be clean, dry and free of oil, grease and other contaminants.

## TECHNICAL DATA

<b>VOLUME SOLIDS</b>	100% (mixed) †								
<b>RECOMMENDED DFT</b>	<b>Horizontal:</b> 6.0 to 12.0 mils (150 to 305 microns) per coat. <b>Vertical:</b> 4.0 to 8.0 mils (100 to 205 microns) per coat. Additional coats may be required for appearance or hiding.								
<b>CURING TIME</b>	<table border="1"> <thead> <tr> <th>Temperature</th> <th>To Topcoat</th> <th>To Place in Service •</th> <th>Full Cure</th> </tr> </thead> <tbody> <tr> <td>75°F (24°C)</td> <td>8-24 hours</td> <td>24 hours</td> <td>5 days</td> </tr> </tbody> </table> <p>If more than 24 hours have elapsed between coats, the Tnemec-Glaze coated surface must be mechanically abraded before topcoating. • <b>Note:</b> 24 hour cure provides for traffic, secondary containment and certain mild chemical exposures. Up to five days cure is required for certain severe chemical exposures. Contact your Tnemec representative or Tnemec Technical Services.</p>	Temperature	To Topcoat	To Place in Service •	Full Cure	75°F (24°C)	8-24 hours	24 hours	5 days
Temperature	To Topcoat	To Place in Service •	Full Cure						
75°F (24°C)	8-24 hours	24 hours	5 days						
<b>VOLATILE ORGANIC COMPOUNDS</b>	<b>Unthinned:</b> 0.19 lbs/gallon (23 grams/litre) <b>Thinned 5% (No. 2 Thinner):</b> 0.52 lbs/gallon (63 grams/litre) <b>Thinned 5% (No. 42 Thinner):</b> 0.50 lbs/gallon (60 grams/litre) †								
<b>THEORETICAL COVERAGE</b>	1,604 mil sq ft/gal (39.4 m <sup>2</sup> /L at 25 microns). See APPLICATION for coverage rates. †								

# TNEME-GLAZE | SERIES 282

**NUMBER OF COMPONENTS** Two: Part A and Part B (1 Part A to 1 Part B by volume)  
**PACKAGING** KITS CONSIST OF:

	PART A	PART B	When Mixed Yield
Large Kit	5 gallon pail	5 gallon pail	10 gallons (37.9 L)
Small Kit	1 gallon can	1 gallon pail	2 gallons (7.57 L)

**NET WEIGHT PER GALLON** 11.51 ± 0.25 lbs (5.2 ± .11 kg) mixed †

**STORAGE TEMPERATURE** Minimum 40°F (4°C) Maximum 90°F (32°C)  
**Note:** Material should be stored at temperatures between 70°F and 90°F (21°C and 32°C) for at least 48 hours prior to use.

**TEMPERATURE RESISTANCE** (Dry) Continuous 275°F (135°C) Intermittent 300°F (149°C)

**SHELF LIFE** 12 months at recommended storage temperature.

**FLASH POINT - SETA** Part A: 180°F (82°C) Part B: N/A

**HEALTH & SAFETY** This product contains chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.  
**Keep out of the reach of children.**

## APPLICATION

**COVERAGE RATES** Before commencing, obtain and thoroughly read the StrataShield Installation and Application Guide for floors.

	Dry MILS (Microns)	Wet MILS (Microns)	Sq Ft/Gal (m <sup>2</sup> /Gal)
Horizontal	6.0-12.0 (150-305)	6.0-12.0 (150-305)	134-267 (12.4-24.8)
Vertical	4.0-8.0 (100-205)	4.0-8.0 (100-205)	201-401 (18.6-37.3)

Allow for overspray and surface irregularities. Film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. †

**MIXING** Use a variable speed drill with a PS Jiffy blade. Slowly mix 1 part A component, and while under agitation add 1 part B component and mix for a minimum of two minutes. Ensure that all Part B is blended with Part A by scraping the pail walls with a flexible spatula. Apply the mixed material within pot life limits after agitation.  
**Note:** A large volume of material will set up quickly if not applied or reduced in volume.  
**Caution: Do not reseal mixed material. An explosion hazard may be created.**

**THINNING** Normally not required. May thin up to 5% or 6.4 ounces (190 mL) per gallon to improve application properties. Brush and roll application use No. 2 Thinner. Spray application use No. 42 Thinner.

**POT LIFE** 25 to 30 minutes at 75°F (24°C) 15 to 20 minutes at 80°F (27°C) 8 to 10 minutes at 90°F (32°C)  
 Material temperatures above 90°F (32°C) will significantly reduce the pot life.

**APPLICATION EQUIPMENT** Brush, roller, squeegee and airless spray.

### Airless Spray

Pump	Tip Orifice	Atomizing Pressure	Mat'l Hose ID	Manifold Filter
Graco "King" 45:1 or 56:1	0.019"-0.033" (485-840 microns)	4,000-5,000 psi (274-344 bar)	3/8" to 1/2" (9.5 to 12.7 mm)	60 mesh (250 microns)

**Roller:** Use high quality 3/8" to 1/2" shed resistant, synthetic woven nap roller cover.

**Brush:** Use high quality synthetic or nylon bristle brush.

**Horizontal:** Squeegee and backroll. Brush small areas only.

**Vertical:** Roll or spray and backroll. Brush small areas only. **Spraying should only be considered as a means to transfer the material to the surface and should be followed by backrolling.**

**SURFACE TEMPERATURE** Minimum of 55°F (13°C), optimum 65°F to 80°F (18°C to 27°C), maximum of 90°F (32°C). The substrate temperature should be at least 5°F (3°C) above the dew point. To avoid outgassing, concrete temperature should be stabilized or in a descending temperature mode. Material should not be applied in direct sunlight.

**MATERIAL TEMPERATURE** For optimum application, handling and performance, the material temperature during application should be between 70°F and 90°F (21°C and 32°C). Temperature will affect the workability. Cool temperatures increase viscosity and decrease workability. Warm temperatures will decrease viscosity and shorten pot life.

**CLEANUP** Flush and clean all equipment immediately after use with xylene or MEK.

† Values may vary with color.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.